

Model		Volatile ≤%	chloride %	S%	mooney viscosity ML1+4, 100°C	tensile strength MPa ≥	elongation %≥	usage
40 type	top	1.0	33~37	0.8~1.2	40~60	25.0	450	every kind of automotive hose, special hose, seal, oil seal products, wire and cable, rubber compound, special rubber roller, special tape and special rubber products
	grade one	1.5						
	qualified	2.0						
45 type	top	1.0	23~27	0.8~1.2	25~40	25.0	450	magnetic rubber, radiation shield,, high hardness products, floor adhesive, waterproofing roof seal, rubber rollers, specialty tapes, waterproofing membranes and other special rubber products.
	grade one	1.5						
	qualified	2.0						